Anc. Ets. STOOPEN & MEEÛS SINCE 1894
Van Praetstraat 22
2660 Antwerp - Hoboken
Belgium
Phone +32 (0)3 825 00 55
Fax +32 (0)3 825 05 13

# TECHNICAL DATA SHEET



## 1. IDENTIFICATION OF THE SUBSTANCE / PREPARATION

**Product name:** **8511**
**Type:** Natural substance
**Color index:** Natural Ochre : PBr7-77492
**Cas n°:** 12713-03-0
**EINECS n°:** -
**Use:** Colorants (pigments), inorganic

## 2. COMPOSITION / INFORMATION ON INGREDIENTS

| Component | CAS | EINECS | Conc. (%) | Remarks |
|---|---|---|---|---|
| Fe2O3 | 1309-37-1 | 215-168-1 | | |
| Al2O3 | | | | |
| MnO2 | | | | |
| SiO2 | | | | |

## 3.PHYSICAL AND CHEMICAL PROPERTIES (GUIDE VALUES)

**Physical state:** Solid. [powders]
**Colour:** Brown
**Rel. tinting strenght:** +- 5%
**pH:** 5 to 8 [Conc. (% w/w): 5%]
**Density :** 4,6-5,7 g/ml
**Tamped density:** 0,74 g/ml
**Solubility:** Insoluble in the following materials: cold water
**Water soluble content:** <2%
**Moisture content:** 3-4%
**Oil absorption:** 64 g/100ml
**Predom. particle size:** -
**Sieve residue:** -
**Melting point:** -

## 4. PROPERTIES (full tone) - (1-5 scale, except light fastness 1-8 scale)

| | | | |
|---|---|---|---|
| **Light fastness:** | 8 | **Acid resistance:** | 5 |
| **Weatherings fastness:** | 5 | **Alkali resistence:** | 5 |
| **Temperature fastness:** | 180℃ | | |

## 5. GENERAL STORAGE CONDITIONS

**General:** Shelf life is minimum 5 years, if stored under the correct conditions.
**Storage conditions:** Store in a dry place and avoid extreme fluctuations in temperature.
Close bags after use to prevent the absorption of moisture and contamination.

## Notice

***The data given here is based on current knowledge and experience. The purpose of this Technical Datasheet is to describe the products in terms of their properties. The above details do not imply any guarantee concerning composition, properties or performance. The client should test the product, several elements might affect the use and the applications. Existing laws and directives have to be respected by the client under his own responsibility.***